

CPC High Temperature Lithium Complex E.P. Grease

- CPC High Temperature Lithium Complex E.P. Greases contain high quality base oils and special E.P. additives, which can provide excellent high-load property, good oxidation stability, anti-rusting and shear stability under normal operation. They are suitable for being used under high temperature up to 200°C.
- The greases are multi-purpose E.P. grease, have been widely used in bearings of industrial machinery especially under high-temperature, high-load, shock-load, and high-speed operation.
- The greases possess high-temperature, high-load, and continuous lubrication ability, so they can perform good lubrication in vehicles
- The combining use of different brand greases should avoid. In the way of changing from others' brands to the greases, the remained grease kept in system, should be expelled and cleaned out thoroughly.
- Packages: (1) 180 kg drum
 - (2) 15 kg pail
 - (3) 0.4 kg can, 0.4kg*30 case (for No.2)
- The typical data are listed as follow:

| | | | I | l I |
|--|---------|---------|---------|---------|
| NLGI Grade No. | No.0 | No.1 | No.2 | No.3 |
| Dropping Point, °C, D2265 | 272 | 298 | 310 | 325 |
| Penetration, D217 | | | | |
| 60worked, 1/10mm | 362 | 316 | 270 | 250 |
| 10,000worked, 1/10mm | 364 | 323 | 280 | 240 |
| Color, Visual | Dark | Dark | Dark | Dark |
| | Green | Green | Green | Green |
| Oxidation Stability, D942 | | | | |
| 100hrs, Pressure Drop, psi | 2.6 | 3.8 | 4.2 | 4.0 |
| 500hrs, Pressure Drop, psi | 14.7 | 15.1 | 15.0 | 14.8 |
| Copper Corrosion, 100°C, 24hrs, D4048 | 1a | 1a | 1a | 1a |
| Soap Base | Lithium | Lithium | Lithium | Lithium |
| | Complex | Complex | Complex | Complex |
| Water Washout, 79°C, %, D1264 | 1 | 6.1 | 3.6 | 2.4 |
| Timken E.P., OK Load, Lbs., D2509 | 45 | 50 | 50 | 50 |
| Viscosity of Mineral Oil, cSt @100°C, D445 | 19.02 | 19.02 | 19.02 | 19.02 |
| Product No. | LB80800 | LB80801 | LB80802 | LB80803 |

Note: Typical properties are based on standard tests under laboratory conditions. Variations that do not affect product performance are to be expected during normal manufacture. Please consult your local CPC representative if you have any questions.